

PİRİNÇ KÜLÇE - BRASS INGOT

ÖZEL DÖKÜM KÜLÇELER *SPECIAL CASTINGOTS*

KOD <i>(CODE)</i>	Alçak Basınç <i>(Low Pressure)</i>	Enjeksiyon <i>(Injection)</i>
KİMYASAL KOMPOZİSYON <i>CHEMICAL COMPOSITION</i>		
Cu	59.20-60.20	57.50-59.50
Pb	1.20-1.60	2.50- 5.00
Al	0.55-0.70	0.55- 1.00
B	-	
As	-	
Fe	0.15(max)	0.70 (max)
Ni	0.20 (max)	0.50 (max)
Sn	0.20 (max)	0.70 (max)
Mn	0.01 (max)	0.40 (max)
Si	0.01 (max)	0.30 (max)
P	0.01 (max)	-
Mg	0.04 (max)	-
Sb	-	0.05 (max)
Zn	Kalan <i>Remainder</i>	Kalan <i>Remainder</i>
Digerleri <i>(Others)</i>	0.03 (max)	0.10 (max)